

CHARACTERISTICS PORCELAIN (Group Bla)

DATE: 16/02/2022

MODEL:	STUDIO GRIS 1ª	SERIE	STUDIO
	SIZE 32X62,5	CODE	200000000000014659

1.-CLASIFICATION (UNE-EN 14411).

Dry Pressed Ceramics Tiles with low water absorption - Group Bla , $E \leq 0,5\%$ for internal and external floors and walls.

2.-SPECIFICATIONS (UNE-EN 14.411 - ISO13.006)

REQUIREMENTS	STANDARD APPLIED	REQUERIMENTS STANDARD	TEST RESULTS
Dimensions and Surface Quality	ISO 10545-2	---	PASS
Water Absorption	ISO 10545-3	$E \leq 0,5 \%$	PASS
Modulus of Rupture	ISO 10545-4	$\geq 35 \text{ N/mm}^2$	PASS
MOHS	EN 101	(*)	6
Crazing Resistance	ISO 10545-11	(*)	PASS
Resistance to chemicals	ISO 10545-13	Min B	A
- Household chemicals: Ammonium chloride solution 100 g/l		Min B	A
- Swimming pool salts: Sodium Hypochlorite solution 20 mg/l			
- Acids and alkalies:			
Low concentrations: Hydrochloric acid solution (3%)		(*)	LA
Citric acid solution 100 g/l		(*)	LA
Potassium hydroxide 30 g/l		(*)	LA
High concentrations: Hydrochloric acid solution (18%)		(*)	HA
Lactic acid solution (5%)		(*)	HA
Potassium hydroxide 100 g/l		(*)	HA
Resistance to staining:	ISO 10545-14	Min 3	5
Cr2O3/FE2O3 + light oil			
Abrasion Resistance (PEI):	ISO 10545-7	(*)	IV
Frost Resistance	ISO 10545-12	Required	PASS
Slip resistance	DIN 51130 (R)	(*)	R10
	ANSI 137.1 (DCOF)	(*)	$,42 < \text{DCOF} < 0,6$
	UNE-ENV 12633(Class)	(*)	1

3.-APLICACION GROUPS

According to its characteristics, Hijos de F. Gaya Fores, defines this model as group:

GRUPO D

(*) as manufacturer confirms



R+D Manager



Operation Manager

GAYAFORES
 HIJOS DE FRANCISCO GAYA FORES, S.L.
 C.I.F. B-12003554
 CV-20, Km. 7 12200 ONDA (Castellón) SPAIN
 Tel. +34 964 62 62 62 info@gayafores.es

1.- CLASSIFICATION. ISO 13006

Water abs. / Production	Group I E ≤ 3 %	Group IIa 3 % < E ≤ 6 %	Group IIb 6 % < E ≤ 10 %	Group III E > 10 %
A Extruded	Group AIa E ≤ 0,5% (Annex M)	Group AIa-1 (Annex B)	Group AIb-1 (Annex D)	Group AIII (Annex F)
	Group AIb 0,5% < E ≤ 3% (Annex A)	Group AIa-2 (Annex C)	Group AIb-2 (Annex E)	
B Dry pressed	Group BIa E ≤ 0,5 % (Annex G)	Group BIa (Annex J)	Group BIb (Annex K)	Group BIII (Annex L)
	Group BIb 0,5 < E ≤ 3 % (Annex H)			

2.-CHARACTERISTICS

RESISTANCE TO	CLASS	MEANING	
Stains	5	The stain is removed with hot water and a damp cloth	
	4	The stain is removed with a weak cleaning agent.	
	3	The stain is removed with mechanical cleaning and a strong cleaning agent	
	2	The stain is removed with suitable solvent after immersion for 24 h.	
	1	The stain is not removed	
Household chemicals Swimming pool salts	A(V) B(V) C(V)	Non Visible effect (if the hue becomes slightly different, this is Definite change in appearance Partial or complete loss of the original surface	
Acids and alkalis	Low concentrations (L)	LA(V)	Non Visible effect (if the hue becomes slightly different, this is
		LB(V)	Definite change in appearance
		LC(V)	Partial or complete loss of the original surface
	High concentrations (H)	HA(V)	Non Visible effect (if the hue becomes slightly different, this is
		HB(V)	Definite change in appearance
		HC(V)	Partial or complete loss of the original surface

3.- APPLICATIONS GROUPS

- GROUP A.-** Recommended for moderate or low level transit. Suitable for bedrooms and/or bathrooms in houses (avoid any kind of abrasion).
- GROUP B.-** Suitable for light or medium transit, such as rooms inside houses, except for kitchens or areas with direct access from outside.
- GROUP C.-** Floorings recommended for medium transit, suitable for houses, all kind of rooms included kitchen or near to entrance areas.
- GROUP D.-** Flooring suitable for heavy traffic, such as entrances to houses with direct access from the outside, all kind of rooms and professional offices.
- GROUP GRAN TRANSITO.-** Flooring suitable and recommended for very heavy traffic
- GROUP E.-** Flooring suitable only for OUTDOORS not roofed (with risk of presence of water). IT IS NEVER RECOMMENDED TO BE INSTALLED INDOORS.
- GROUP W.-** Tiles suitable only for laying in wall coverings.

REMARKS:
