

DESCRIPTION

Total thickness	EN ISO24346	mm	2.60	2.60	2.60
Wearlayer thickness	EN ISO24340	mm	0.25	0.25	0.25
Poids	EN ISO 23997	g/m ²	1500	1725	1725
Weight	EN ISO 24341	cm	200 / 300 / 400		
Width of sheet	EN ISO 24341	ml	≈ 30		

CLASSIFICATION

Norm / Product specification	-	-	EN ISO 26986		
European classification	EN ISO 10874	class	22		
Impact sound insulation	EN ISO 717-2	dB	19		
Walk noise	NFS 31 074	dB	≤ 65		
Fire rating	EN 13 501-1	class	Cfls1		
Static electrical propensity	EN 1815	kV	< 2		
Slip resistance wet : ramp test with oil	DIN 51130	class	-	R10	R10



PERFORMANCE

Wear group	-	group	T		
Dimensional stability (requirement)	EN ISO 23999	%	≤ 0.40		
Dimensional stability (average measured value)	-	%	0.05		
Residual indentation (requirement)	EN ISO 24343-2	mm	≤ 0.35		
Residual indentation (average value measured)		mm	0.25		
Thermal conductivity	EN ISO 10456	W/(m.K)	0.25		
Colour fastness	EN 20 105 - B02	degree	≥ 6		
Surface treatment	-	-	Diamalite	Diamalite	Pureclean
Chemical products resistance	EN ISO 26987	class	ok		

ENVIRONMENT / INDOOR AIR QUALITY

TVOC after 28 days	ISO 16000-6	µg/ m ³	< 100		
Certification	-	-	Floorscore®		

CE MARKING

	EN 14041	-			
		-	