


DESCRIPTION			DESIGN	PRIME
Total thickness	EN ISO 24346	mm	1.50	1.30
Thickness of wear layer	EN ISO 24340	mm	0.08	0.08
Weight	EN ISO 23997	g/m ²	2550	2190
Size	EN ISO 24342	mm	305 X 305	305 x 305
Number of planks / tiles and sqm per box	-	-	11 / 1m ²	11 / 1m ²
CLASSIFICATION				
Norm / Product specification	-	-	EN ISO 10582	
European classification	EN ISO 10874	class	22	
Fire rating	EN 13 501-1	class	B _{fl} -s1	
Static electrical propensity	EN 1815	kV	< 2	
Slip resistance wet	EN 16165:2021	class	R9 – R10	
PERFORMANCES				
Wear Resistance	EN 660.2	mm ³	≤ 2.0	
Wear Group	-	group	T	
Type Binder content	EN ISO 10582	type	I	
Dimensional stability	EN ISO 23999	%	≤ 0.40	
Residual indentation	EN ISO 24343-1	mm	≤ 0.10	
Sound insulation	EN ISO 717-2	dB	3	
Room impact noise	NFS 31074	dB	80	
Castor chair test (Type W)	ISO 4918	-	-	
Thermal conductivity	EN ISO 10456	W/(m.K)	0.25	
Colour fastness	EN ISO 105 - B02	degree	≥ 6	
ENVIRONMENT – INDOOR AIR QUALITY				
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 100	
CE MARKING				
	EN 14041		