

**DESCRIPTION**

|                     |              |                  |                 |
|---------------------|--------------|------------------|-----------------|
| Total thickness     | EN ISO24346  | mm               | 2.90            |
| Wearlayer thickness | EN ISO24340  | mm               | 0.35            |
| Poids               | EN ISO 23997 | g/m <sup>2</sup> | 2000            |
| Weight              | EN ISO 24341 | cm               | 200 / 300 / 400 |
| Width of sheet      | EN ISO 24341 | ml               | ≈ 25            |

**CLASSIFICATION**

|  |              |       |              |
|--|--------------|-------|--------------|
| Norm / Product specification             | -            | -     | EN ISO 26986 |
| European classification                  | EN ISO 10874 | class | 23 - 32      |
| Impact sound insulation                  | EN ISO 717-2 | dB    | 16           |
| Walk noise                               | NFS 31 074   | dB    | ≤ 65         |
| Fire rating                              | EN 13 501-1  | class | Cfls1        |
| Static electrical propensity             | EN 1815      | kV    | < 2          |
| Slip resistance wet : ramp test with oil | DIN 51130    | class | R10          |






**PERFORMANCE**

|  |                 |         |           |
|--|-----------------|---------|-----------|
| Wear group                                     | -               | group   | T         |
| Dimensional stability (requirement)            | EN ISO 23999    | %       | ≤ 0.40    |
| Dimensional stability (average measured value) | -               | %       | 0.05      |
| Residual indentation (requirement)             | EN ISO 24343-2  | mm      | ≤ 0.35    |
| Residual indentation (average value measured)  |                 | mm      | 0.20      |
| Thermal conductivity                           | EN ISO 10456    | W/(m.K) | 0.25      |
| Colour fastness                                | EN 20 105 - B02 | degree  | ≥ 6       |
| Surface treatment                              | -               | -       | Pureclean |
| Chemical products resistance                   | EN ISO 26987    | class   | ok        |

**ENVIRONMENT / INDOOR AIR QUALITY**

|                    |             |                    |             |
|--------------------|-------------|--------------------|-------------|
| TVOC after 28 days | ISO 16000-6 | µg/ m <sup>3</sup> | < 100       |
| Certification      | -           | -                  | Floorscore® |

**CE MARKING**

|   |          |   |   |
|---|----------|---|---|
|  | EN 14041 | - |    |
|   |          | - |    |